

# Metal Powders USA

## Technical Information

### WHITE BRONZE POWDER -325 Mesh

#### NOMINAL CHEMISTRY:

	RESULT	MIN	MAX	TEST METHOD
ZINC, %	20.43	20	24	SPECTRO
TIN, %	27.02	26	30	
COPPER, %	BALANCE	BALANCE		

#### SCREEN ANALYSIS:

Mesh		%
-140/+200		TRACE
-200/+325		5 Max.
-325		99.5 Max.

MPIF STD 05

APPARENT DENSITY (G/CC)

2.8 Min.

MPIF STD 28

The information on this data sheet is based on our research and the research of others, and is believed to be accurate. No guarantee of their accuracy is made, however, and the products which are mentioned are sold without warranty, express or implied, and upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes. Likewise, statements concerning these products or methods for their use are not intended as authorizing or recommending their manufacture, use or sale in infringement of any patent.