

SIEVE ANALYSIS NO. 4 coarse Agg  
C - 136

SIEVE SIZE	Accumulative	Accumulative	Accumulative	Project
U.S./METRIC	weight retained	% retained	% passing	Specification
2" / 50mm	0	0	100	100
1.5" / 37.5mm	0.48	0.8	99	90-100
1" / 25.0mm	28.18	48.5	52	20-55
3/4" / 19.0mm	52.82	90.8	9	0-15
1/2" / 12.5mm	56.94	97.9	2	—
3/8" / 9.5mm	57.4	98.7	1	0-5
#4 / 4.75mm		0.0	100	—
#8 / 2.36mm		0.0	100	—
#16 / 1.18mm		0.0	100	
#30 / 600mm		0.0	100	
#50 / 300mm		0.0	100	
#100 / 150mm		0.0	100	
#200 / 75mm		0.0	100.0	
pan	58.14			

%Moisture	
Agg wet weight	58.2
Agg dry weight	58.1
Moisture loss	0.1
% moisture	0.1

**Min Agg Sample Size of 33 lbs**