

Aggregate Analysis

601	602	603	604	605	606	607	608	609
Greeley	Windsor	Firestone	Ft. Lupton	Milliken	Denver	Jeffco	Henderson	Titan

Sample Date: 18-Jan-24
 Sample No: 70640
 Product: 1 1/2" - Jeffco

Seive Size	Cum. Wt.	% Retained	% Passing	#4 Spec				
2"	0.0	0.0	100.0	100				
1-1/2"	1.1	3.0	97.0	90 - 100				
1"	22.2	57.0	43.0	20 - 55				
3/4"	37.3	96.0	4.0	0 - 15				
1/2"	38.8	99.7	0.3	-				
3/8"	38.9	100.0	0.0	0 - 5				
Seive Size				Seive Size				
No. 4								
No. 8								
Pan								

Weight of Sample: 38.9
 % Discrepancy: _____
 Sand Equivalency (SE): _____
 Fineness Modulus: _____

Mass Dry Before #200 Wash: _____
 Mass Dry After #200 Wash: _____
 Difference: _____
 % (-) #200: _____

Notes:

Sample Passes Spec.